IN THE CLAIMS

1. (original): A process for forming an image on a substrate comprising applying an ink thereto by means of an ink-jet printer wherein the ink comprises a liquid medium and a phthalocyanine dye fraction obtainable by the fractionation of a solution and/or suspension of a mixture of phthalocyanine dyes of Formula (1), and salts thereof, by cross-flow filtration:

$$\mathsf{MPc} \underbrace{ \left(\mathsf{SO_3H} \right)_x}_{\left(\mathsf{SO_2NR}^{1}\mathsf{R}^{2} \right)_y}$$

$$\underbrace{ \left(\mathsf{SO_2NR}^{3}\mathsf{R}^{4} \right)_z}_{\left(\mathsf{SO_2NR}^{3}\mathsf{R}^{4} \right)_z}$$

Formula (1)

wherein:

M is 2H, copper or nickel;

Pc represents a phthalocyanine nucleus;

R¹ and R³ independently are H or optionally substituted C₁₋₄alkyl;

R² and R⁴ independently are H or optionally substituted hydrocarbyl; or R¹ and R², and, R³ and R⁴, independently, together with the nitrogen atom to which they are attached represent an optionally substituted aliphatic or aromatic ring system;

x is 0 to 3.9;

y is 0 to 3.9;


z is 0.1 to 4; and

the sum of (x+y+z) is 2.4 to 4.5.

- 2. (original): A process according to claim 1 wherein the substrate is paper.
- 3. (original): A process according to either claim 1 or claim 2 wherein the substrate is photographic quality paper.

- 4. (currently amended): A process according to any one of the preceding claims claim 1 wherein the ink has a viscosity of less than 20cP at 25°C; contains less than 500ppm in total of divalent and trivalent metal ions (other than any divalent and trivalent metal ions bound to a component of the ink); contains less than 500ppm halide ions; and has been filtered through a filter having a mean pore size below 10μm.
- 5. (currently amended): A process according to any one of the preceding claims claim 1 where in the mixture of phthalocyanine dyes of Formula (1) M is Cu.
- 6. (currently amended): A process according to any one of the preceding claims claim 1 where in the mixture of phthalocyanine dyes of Formula (1) R¹, R², and R³ are all H and R⁴ is hydroxyethyl.
- 7. (currently amended): A process according to any one of the preceding claims claim 1 where in the mixture of phthalocyanine dyes of Formula (1) R³ is H, R⁴ is carboxyphenyl and y is 0.
- 8. (currently amended): A process according to any one of the preceding claims claim 1 where in the mixture of phthalocyanine dyes of Formula (1) R³ and R⁴ are both H and y is 0.
- 9. (currently amended): A process according to any one of the preceding claims claim 1 wherein the cross-flow filtration membrane is an ultrafiltration membrane.
- 10. (original): A process according to claim 9 wherein the ultrafiltration membrane has a nominal molecular weight cut-off in the range of from 5,000 to 500,000.
- 11. (currently amended): A process according to either claim 9 or claim 10 wherein the ultrafiltration membrane has a nominal molecular weight cut-off in the range of from 20,000 to 100,000.
- 12. (currently amended): A process according to any one of the preceding claims claim 1 or claim 9 wherein cross-flow filtration is through a series of 2 or more membranes.

- 13. (currently amended): A printed substrate obtainable by means of a process as described in any one of claims 1 to 12 claim 1.
- 14. (original): A printed substrate according to claim 13 which comprises paper.
- 15. (original): A printed substrate according to either claim 13 or claim 14 which is a photographic quality print.
- 16. (original): An ink-jet printing ink that comprises:
 - i) a phthalocyanine dye fraction obtainable by the fractionation of a solution and/or suspension of a mixture of phthalocyanine dyes of Formula (1) and salts thereof by cross-flow filtration :



Formula (1)

wherein:

M is 2H, copper or nickel;

Pc represents a phthalocyanine nucleus;

R¹ and R³ independently are H or optionally substituted C₁₋₄alkyl;

R² and R⁴ independently are H or optionally substituted hydrocarbyl; or

R¹ and R², and, R³ and R⁴, independently, together with the nitrogen atom to which they are attached represent an optionally substituted aliphatic or aromatic ring system;

x is 0 to 3.9;

y is 0 to 3.9;

z is 0.1 to 4; and

the sum of (x+y+z) is 4; and

(ii) a liquid medium:

New Patent Application of Graham Michael WATSON et al. Attorney Docket No. 066079-5138-US

wherein the ink has a viscosity of less than 20cP at 25°C; contains less than 500ppm in total of divalent and trivalent metal ions (other than any divalent and trivalent metal ions bound to a component of the ink); contains less than 500ppm halide ions; and has been filtered through a filter having a mean pore size below 10µm.

17. (original): An ink-jet printer cartridge comprising a chamber and an ink wherein the ink is in the chamber and the ink is as defined in claim 16.